

ABL(STEVENS)Resin & glass
Unit 4, Millbuck Way
Springvale Industrial estate
Sandbach, Cheshire, CW11 3HT
Tel:01270 766685/529111
www.resin-supplies.co.uk

Technical Data

CLEAR BRUSHING GELCOAT

Description	Clear, isophthalic brushing polyester gelcoat (standard viscosity)
Product use	General purpose, high quality moulding gelcoat for hand lay-up in GRP work.
Characteristics	For brush application, free from air and can be used clear or pigmented with high quality pigment pastes. The product is free from drainage and has excellent weathering properties as well as very good water resistance.
Application	Should be used in workshop temperatures between 16 - 23°C and requires the addition of 2% Medium activity MEKP for a sufficient cure. For best results, the gelcoat should be applied to a clean polished mould in one even layer 400 – 500 microns (0.4 – 0.5 mm thickness).

Liquid gelcoat properties

Appearance	Translucent, blue liquid
Liquid properties	Thixotropic
Gel time 2% medium activity MEKP @ 25°C	< 15 minutes